

(detailed below), with a continuous cast steel chemistry of type MR, with a surface finish of type 7B or 7C, with a surface passivation of 0.5 mg/square foot of chromium applied as a cathodic dichromate treatment, with ultra flat scroll cut sheet form, with CAT5 temper with 1.00/0.10 pound/base box coating, with a lithograph logo printed in a uniform pattern on the 0.10 pound coating side with a clear protective coat, with both sides waxed to a level of 15–20 mg/216 sq. inch, with ordered dimension combinations of (1) 75 pound/base box (0.0082 inch) thickness and 34.9375 inch x 31.748 inch scroll cut dimensions; or (2) 75 pound/base box (0.0082 inch) thickness and 34.1875 inch x 29.076 inch scroll cut dimensions; or (3) 107 pound/base box (0.0118 inch) thickness and 30.5625 inch x 34.125 inch scroll cut dimension.

- Tin-free steel coated with a metallic chromium layer between 100–200 mg/m² and a chromium oxide layer between 5–30 mg/m²; chemical composition of 0.05% maximum carbon, 0.03% maximum silicon, 0.60% maximum manganese, 0.02% maximum phosphorous, and 0.02% maximum sulfur; magnetic flux density (Br) of 10 kg minimum and a coercive force (Hc) of 3.8 Oe minimum.

- Tin-free steel laminated on one or both sides of the surface with a polyester film, consisting of two layers (an amorphous layer and an outer crystal layer), that contains no more than the indicated amounts of the following environmental hormones: 1 mg/kg BADGE (BisPhenol—A Di-glycidyl Ether), 1 mg/kg BFDGE (BisPhenol—F Di-glycidyl Ether), and 3 mg/kg BPA (BisPhenol—A).

The merchandise subject to this investigation is currently classified in the Harmonized Tariff Schedule of the United States (HTSUS), under HTSUS subheadings 7210.11.0000, 7210.12.0000, 7210.50.0020, 7210.50.0090, 7212.10.0000, and 7212.50.0000 if of non-alloy steel and under HTSUS subheadings 7225.99.0090, and 7226.99.0180 if of alloy steel. Although the subheadings are provided for convenience and customs purposes, the written description of the scope of the investigation is dispositive.

Appendix II

List of Topics Discussed in the Preliminary Decision Memorandum

- I. Summary
- II. Background
- III. Period of Investigation
- IV. Scope of the Investigation
- V. Affiliation
- VI. Discussion of the Methodology
- VII. Currency Conversion
- VIII. Recommendation

[FR Doc. 2023–18035 Filed 8–21–23; 8:45 am]

BILLING CODE 3510–DS–P

DEPARTMENT OF COMMERCE

International Trade Administration

[A–421–816]

Tin Mill Products From the Netherlands: Preliminary Negative Determination of Sales at Less Than Fair Value and Postponement of Final Determination

AGENCY: Enforcement and Compliance, International Trade Administration, Department of Commerce.

SUMMARY: The U.S. Department of Commerce (Commerce) preliminarily determines that tin mill products from the Netherlands are not being, or are not likely to be, sold in the United States at less than fair value (LTFV). The period of investigation is January 1, 2022, through December 31, 2022. Interested parties are invited to comment on this preliminary determination.

DATES: Applicable August 22, 2023.

FOR FURTHER INFORMATION CONTACT: Brittany Bauer, AD/CVD Operations, Office V, Enforcement and Compliance, International Trade Administration, U.S. Department of Commerce, 1401 Constitution Avenue NW, Washington, DC 20230; telephone: (202) 482–3860.

SUPPLEMENTARY INFORMATION:

Background

This preliminary determination is made in accordance with section 733(b) of the Tariff Act of 1930, as amended (the Act). Commerce published the notice of initiation of this LTFV investigation on February 14, 2023.¹ On May 31, 2023, Commerce postponed the preliminary determination of this investigation, and the revised deadline is now August 16, 2023.² For a complete description of the events that followed the initiation of this investigation, see the Preliminary Decision Memorandum.³ A list of topics included in the Preliminary Decision Memorandum is included as Appendix II to this notice. The Preliminary

¹ See *Tin Mill Products from Canada, the People's Republic of China, Germany, the Netherlands, the Republic of Korea, Taiwan, the Republic of Turkey, and the United Kingdom: Initiation of Less-Than-Fair-Value Investigations*, 88 FR 9481 (February 14, 2023) (*Initiation Notice*).

² See *Tin Mill Products from Canada, the People's Republic of China, Germany, the Netherlands, the Republic of Korea, Taiwan, the Republic of Turkey, and the United Kingdom: Postponement of Preliminary Determinations in the Less-Than-Fair-Value Investigations*, 88 FR 34827 (May 31, 2023).

³ See Memorandum, “Decision Memorandum for the Preliminary Negative Determination of Sales at Less-Than-Fair-Value in the Investigation of Tin Mill Products from the Netherlands,” dated concurrently with, and hereby adopted by, this notice (Preliminary Decision Memorandum).

Decision Memorandum is a public document and is on file electronically via Enforcement and Compliance’s Antidumping and Countervailing Duty Centralized Electronic Service System (ACCESS). ACCESS is available to registered users at <https://access.trade.gov>. In addition, a complete version of the Preliminary Decision Memorandum can be accessed directly at <https://access.trade.gov/public/FRNoticesListLayout.aspx>.

Scope of the Investigation

The products covered by this investigation are tin mill products from the Netherlands. For a complete description of the scope of this investigation, see Appendix I.

Scope Comments

In accordance with the preamble to Commerce’s regulations,⁴ in the *Initiation Notice*, Commerce set aside a period of time for parties to raise issues regarding product coverage (*i.e.*, scope).⁵ Certain interested parties commented on the scope of the investigation as it appeared in the *Initiation Notice*. For a summary of the product coverage comments and rebuttal responses submitted to the record for this investigation, and accompanying discussion and analysis of all comments timely received, see the Preliminary Scope Decision Memorandum.⁶ As discussed in the Preliminary Scope Decision Memorandum, Commerce preliminarily did not modify the scope language as it appeared in the *Initiation Notice*. In the Preliminary Scope Decision Memorandum, Commerce established the deadline for parties to submit scope case and rebuttal briefs.

Methodology

Commerce is conducting this investigation in accordance with section 731 of the Act. Commerce calculated export prices and constructed export prices in accordance with sections 772(a) and 772(b) of the Act. Normal value is calculated in accordance with section 773 of the Act. For a full description of the methodology underlying the preliminary determination, see the Preliminary Decision Memorandum.

Preliminary Determination

Commerce preliminarily determines that the following estimated weighted-average dumping margin exists:

⁴ See *Antidumping Duties; Countervailing Duties, Final Rule*, 62 FR 27296, 27323 (May 19, 1997).

⁵ See *Initiation Notice*, 88 FR at 9482.

⁶ See Memorandum, “Preliminary Scope Decision Memorandum,” dated concurrently with this notice (Preliminary Scope Decision Memorandum).

Exporter/producer	Estimated weighted-average dumping margin (percent)
Tata Steel IJmuiden BV	0.00

Consistent with section 733(b)(3) of the Act, Commerce disregards *de minimis* rates. Accordingly, Commerce preliminarily determines that TSIJ, the only individually examined respondent, has not made sales of subject merchandise at LTFV.

Consistent with section 733(d) of the Act, Commerce has not calculated an estimated weighted-average dumping margin for all other producers and exporters because it has not made an affirmative preliminary determination of sales at LTFV.

Suspension of Liquidation

Because Commerce has made a negative preliminary determination of sales at LTFV with regard to subject merchandise, Commerce will not direct U.S. Customs and Border Protection to suspend liquidation or to require a cash deposit of estimated antidumping duties for entries of tin mill products from the Netherlands.

Disclosure

Commerce intends to disclose its calculations and analysis performed to interested parties in this preliminary determination within five days of any public announcement or, if there is no public announcement, within five days of the date of publication of this notice in the **Federal Register**, in accordance with 19 CFR 351.224(b).

Verification

As provided in section 782(i)(1) of the Act, Commerce intends to verify the information relied upon in making its final determination.

Public Comment

Case briefs or other written comments on non-scope issues may be submitted to the Assistant Secretary for Enforcement and Compliance no later than seven days after the date on which the last verification report is issued in this investigation. Rebuttal briefs, limited to issues raised in case briefs, may be submitted no later than seven days after the deadline date for case briefs.⁷ Note that Commerce has temporarily modified certain of its requirements for serving documents containing business proprietary

⁷ See 19 CFR 351.309; see also 19 CFR 351.303 (for general filing requirements).

information, until further notice.⁸ Pursuant to 19 CFR 351.309(c)(2) and (d)(2), parties who submit case briefs or rebuttal briefs in this investigation are encouraged to submit with each argument: (1) a statement of the issue; (2) a brief summary of the argument; and (3) a table of authorities.

Pursuant to 19 CFR 351.310(c), interested parties who wish to request a hearing, limited to issues raised in the case and rebuttal briefs, must submit a written request to the Assistant Secretary for Enforcement and Compliance, U.S. Department of Commerce, within 30 days after the date of publication of this notice in the **Federal Register**. Requests should contain the party's name, address, and telephone number, the number of participants, whether any participant is a foreign national, and a list of the issues to be discussed. If a request for a hearing is made, Commerce intends to hold the hearing at a time and date to be determined. Parties should confirm by telephone the date, time, and location of the hearing two days before the scheduled date.

Postponement of Final Determination

Section 735(a)(2)(B) of the Act provides that a final determination may be postponed until not later than 135 days after the date of the publication of the preliminary determination in the **Federal Register** if, in the event of a negative preliminary determination, a request for such postponement is made by the petitioners.

On July 28, 2023, Cleveland-Cliffs Inc. and the United Steel, Paper and Forestry, Rubber, Manufacturing, Energy, Allied Industrial and Service Workers International Union (collectively, the petitioners) requested that Commerce postpone the final determination in the event of a negative preliminary determination.⁹ In accordance with section 735(a)(2)(B) of the Act, and 19 CFR 351.210(b)(2)(i), because: (1) the preliminary determination is negative; (2) the petitioners have requested the postponement of the final determination; and (3) no compelling reasons for denial exist, Commerce is postponing the final determination. Accordingly, Commerce will make its final determination by no later than 135 days after the date of publication of this preliminary determination in the

⁸ See *Temporary Rule Modifying AD/CVD Service Requirements Due to COVID-19; Extension of Effective Period*, 85 FR 41363 (July 10, 2020).

⁹ See Petitioners Letter, "Petitioners' Request For Postponement Of The Final Determinations," dated July 28, 2023.

Federal Register, pursuant to section 735(a)(2) of the Act.¹⁰

U.S. International Trade Commission Notification

In accordance with section 733(f) of the Act, Commerce will notify the U.S. International Trade Commission (ITC) of its preliminary determination. If the final determination is affirmative, the ITC will determine 75 days after the final determination whether imports of tin mill products from the Netherlands are materially injuring, or threaten material injury to, the U.S. industry.

Notification to Interested Parties

This determination is issued and published in accordance with sections 733(f) and 777(i)(1) of the Act, and 19 CFR 351.205(c).

Dated: August 16, 2023.

Lisa W. Wang,

Assistant Secretary for Enforcement and Compliance.

Appendix I

Scope of the Investigation

The products within the scope of this investigation are tin mill flat-rolled products that are coated or plated with tin, chromium, or chromium oxides. Flat-rolled steel products coated with tin are known as tinplate. Flat-rolled steel products coated with chromium or chromium oxides are known as tin-free steel or electrolytic chromium-coated steel. The scope includes all the noted tin mill products regardless of thickness, width, form (in coils or cut sheets), coating type (electrolytic or otherwise), edge (trimmed, untrimmed or further processed, such as scroll cut), coating thickness, surface finish, temper, coating metal (tin, chromium, chromium oxide), reduction (single- or double-reduced), and whether or not coated with a plastic material.

All products that meet the written physical description are within the scope of this investigation unless specifically excluded. The following products are outside and/or specifically excluded from the scope of this investigation:

- Single reduced electrolytically chromium coated steel with a thickness 0.238 mm (85 pound base box) ($\pm 10\%$) or 0.251 mm (90 pound base box) ($\pm 10\%$) or 0.255 mm ($\pm 10\%$) with 770 mm (minimum width) (± 1.588 mm) by 900 mm (maximum length if sheared) sheet size or 30.6875 inches (minimum width) ($\pm 1/16$ inch) and 35.4 inches (maximum length if sheared) sheet size; with type MR or higher (per ASTM) A623 steel chemistry; batch annealed at T2 1/2 anneal temper, with a yield strength of 31 to 42 kpsi (214 to 290 Mpa); with a tensile strength of 43 to 58 kpsi (296 to 400 Mpa); with a chrome coating restricted to 32 to 150 mg/m²; with a chrome oxide coating restricted to 6 to 25 mg/m² with a modified 7B ground roll finish or blasted roll finish; with roughness average (Ra) 0.10 to 0.35 micrometers,

¹⁰ See also 19 CFR 351.210(e).

measured with a stylus instrument with a stylus radius of 2 to 5 microns, a trace length of 5.6 mm, and a cut-off of 0.8 mm, and the measurement traces shall be made perpendicular to the rolling direction; with an oil level of 0.17 to 0.37 grams/base box as type BSO, or 2.5 to 5.5 mg/m² as type DOS, or 3.5 to 6.5 mg/m² as type ATBC; with electrical conductivity of static probe voltage drop of 0.46 volts drop maximum, and with electrical conductivity degradation to 0.70 volts drop maximum after stoving (heating to 400 degrees F for 100 minutes followed by a cool to room temperature).

- Single reduced electrolytically chromium- or tin-coated steel in the gauges of 0.0040 inch nominal, 0.0045 inch nominal, 0.0050 inch nominal, 0.0061 inch nominal (55 pound base box weight), 0.0066 inch nominal (60 pound base box weight), and 0.0072 inch nominal (65 pound base box weight), regardless of width, temper, finish, coating or other properties.

- Single reduced electrolytically chromium coated steel in the gauge of 0.024 inch, with widths of 27.0 inches or 31.5 inches, and with T-1 temper properties.

- Single reduced electrolytically chromium coated steel, with a chemical composition of 0.005% max carbon, 0.030% max silicon, 0.25% max manganese, 0.025% max phosphorous, 0.025% max sulfur, 0.070% max aluminum, and the balance iron, with a metallic chromium layer of 70–130 mg/m², with a chromium oxide layer of 5–30 mg/m², with a tensile strength of 260–440 N/mm², with an elongation of 28–48%, with a hardness (HR-30T) of 40–58, with a surface roughness of 0.5–1.5 microns Ra, with magnetic properties of Bm (kg) 10.0 minimum, Br (kg) 8.0 minimum, Hc (Oe) 2.5–3.8, and MU 1400 minimum, as measured with a Riken Denshi DC magnetic characteristic measuring machine, Model BHU-60.

- Bright finish tin-coated sheet with a thickness equal to or exceeding 0.0299 inch, coated to thickness of $\frac{3}{4}$ pound (0.000045 inch) and 1 pound (0.00006 inch).

- Electrolytically chromium coated steel having ultra flat shape defined as oil can maximum depth of $\frac{5}{64}$ inch (2.0 mm) and edge wave maximum of $\frac{5}{64}$ inch (2.0 mm) and no wave to penetrate more than 2.0 inches (51.0 mm) from the strip edge and coilset or curling requirements of average maximum of $\frac{5}{64}$ inch (2.0 mm) (based on six readings, three across each cut edge of a 24 inches (61 cm) long sample with no single reading exceeding $\frac{1}{32}$ inch (3.2 mm) and no more than two readings at $\frac{1}{32}$ inch (3.2 mm)) and (for 85 pound base box item only: crossbuckle maximums of 0.001 inch (0.0025 mm) average having no reading above 0.005 inch (0.127 mm)), with a camber maximum of $\frac{1}{4}$ inch (6.3 mm) per 20 feet (6.1 meters), capable of being bent 120 degrees on a 0.002 inch radius without cracking, with a chromium coating weight of metallic chromium at 100 mg/m² and chromium oxide of 10 mg/m², with a chemistry of 0.13% maximum carbon, 0.60% maximum manganese, 0.15% maximum silicon, 0.20% maximum copper, 0.04% maximum phosphorous, 0.05% maximum sulfur, and 0.20% maximum aluminum, with a surface

finish of Stone Finish 7C, with a DOS-A oil at an aim level of 2 mg/square meter, with not more than 15 inclusions/foreign matter in 15 feet (4.6 meters) (with inclusions not to exceed $\frac{1}{32}$ inch (0.8 mm) in width and $\frac{3}{64}$ inch (1.2 mm) in length), with thickness/temper combinations of either 60 pound base box (0.0066 inch) double reduced CADR8 temper in widths of 25.00 inches, 27.00 inches, 27.50 inches, 28.00 inches, 28.25 inches, 28.50 inches, 29.50 inches, 29.75 inches, 30.25 inches, 31.00 inches, 32.75 inches, 33.75 inches, 35.75 inches, 36.25 inches, 39.00 inches, or 43.00 inches, or 85 pound base box (0.0094 inch) single reduced CAT4 temper in widths of 25.00 inches, 27.00 inches, 28.00 inches, 30.00 inches, 33.00 inches, 33.75 inches, 35.75 inches, 36.25 inches, or 43.00 inches, with width tolerance of $\frac{1}{8}$ inch, with a thickness tolerance of 0.0005 inch, with a maximum coil weight of 20,000 pounds (9071.0 kg), with a minimum coil weight of 18,000 pounds (8164.8 kg), with a coil inside diameter of 16 inches (40.64 cm) with a steel core, with a coil maximum outside diameter of 59.5 inches (151.13 cm), with a maximum of one weld (identified with a paper flag) per coil, with a surface free of scratches, holes, and rust.

- Electrolytically tin coated steel having differential coating with 1.00 pound/base box equivalent on the heavy side, with varied coating equivalents in the lighter side (detailed below), with a continuous cast steel chemistry of type MR, with a surface finish of type 7B or 7C, with a surface passivation of 0.7 mg/square foot of chromium applied as a cathodic dichromate treatment, with coil form having restricted oil film weights of 0.3–0.4 grams/base box of type DOS-A oil, coil inside diameter ranging from 15.5 to 17 inches, coil outside diameter of a maximum 64 inches, with a maximum coil weight of 25,000 pounds, and with temper/coating/dimension combinations of: (1) CAT4 temper, 1.00/.050 pound/base box coating, 70 pound/base box (0.0077 inch) thickness, and 33.1875 inch ordered width; or (2) CAT5 temper, 1.00/0.50 pound/base box coating, 75 pound/base box (0.0082 inch) thickness, and 34.9375 inch or 34.1875 inch ordered width; or (3) CAT5 temper, 1.00/0.50 pound/base box coating, 107 pound/base box (0.0118 inch) thickness, and 30.5625 inch or 35.5625 inch ordered width; or (4) CADR8 temper, 1.00/0.50 pound/base box coating, 85 pound/base box (0.0093 inch) thickness, and 35.5625 inch ordered width; or (5) CADR8 temper, 1.00/0.25 pound/base box coating, 60 pound/base box (0.0066 inch) thickness, and 35.9375 inch ordered width; or (6) CADR8 temper, 1.00/0.25 pound/base box coating, 70 pound/base box (0.0077 inch) thickness, and 32.9375 inch, 33.125 inch, or 35.1875 inch ordered width.

- Electrolytically tin coated steel having differential coating with 1.00 pound/base box equivalent on the heavy side, with varied coating equivalents on the lighter side (detailed below), with a continuous cast steel chemistry of type MR, with a surface finish of type 7B or 7C, with a surface passivation of 0.5 mg/square foot of chromium applied as a cathodic dichromate treatment, with ultra flat scroll cut sheet form, with CAT5 temper

with 1.00/0.10 pound/base box coating, with a lithograph logo printed in a uniform pattern on the 0.10 pound coating side with a clear protective coat, with both sides waxed to a level of 15–20 mg/216 sq. inch, with ordered dimension combinations of (1) 75 pound/base box (0.0082 inch) thickness and 34.9375 inch × 31.748 inch scroll cut dimensions; or (2) 75 pound/base box (0.0082 inch) thickness and 34.1875 inch × 29.076 inch scroll cut dimensions; or (3) 107 pound/base box (0.0118 inch) thickness and 30.5625 inch × 34.125 inch scroll cut dimension.

- Tin-free steel coated with a metallic chromium layer between 100–200 mg/m² and a chromium oxide layer between 5–30 mg/m²; chemical composition of 0.05% maximum carbon, 0.03% maximum silicon, 0.60% maximum manganese, 0.02% maximum phosphorous, and 0.02% maximum sulfur; magnetic flux density (Br) of 10 kg minimum and a coercive force (Hc) of 3.8 Oe minimum.

- Tin-free steel laminated on one or both sides of the surface with a polyester film, consisting of two layers (an amorphous layer and an outer crystal layer), that contains no more than the indicated amounts of the following environmental hormones: 1 mg/kg BADGE (BisPhenol—A Di-glycidyl Ether), 1 mg/kg BFDGE (BisPhenol—F Di-glycidyl Ether), and 3 mg/kg BPA (BisPhenol—A).

The merchandise subject to this investigation is currently classified in the Harmonized Tariff Schedule of the United States (HTSUS), under HTSUS subheadings 7210.11.0000, 7210.12.0000, 7210.50.0020, 7210.50.0090, 7212.10.0000, and 7212.50.0000 if of non-alloy steel and under HTSUS subheadings 7225.99.0090, and 7226.99.0180 if of alloy steel. Although the subheadings are provided for convenience and customs purposes, the written description of the scope of the investigation is dispositive.

Appendix II

List of Topics Discussed in the Preliminary Decision Memorandum

- I. Summary
- II. Background
- III. Period of Investigation
- IV. Scope of the Investigation
- V. Discussion of the Methodology
- VI. Currency Conversion
- VII. Recommendation

[FR Doc. 2023–18032 Filed 8–21–23; 8:45 am]

BILLING CODE 3510-DS-P